


Specifications

50-07

ISO 10582 Heterogeneous PVC	GB	DE	FR	NL	IT	Loose Lay 50-07
ISO 24340	Thickness of the wear layer	Stärke Nutzschrift	Épaisseur de couche d'usure	Dikte van de slijtlaag	Spessore dello strato di usura	0.7 mm + Polyurethane
ISO 24346:2006	Overall thickness	Gesamtstärke	Épaisseur totale	Totale dikte	Spessore totale	5 mm
ISO 23997:2008	Weight	Gewicht	Poids	Gewicht	Peso	+/- 8.490 kg/m²
ISO 23999:2008	Dimensional stability (average value) In longitudinal direction (%): In cross direction (%):	Dimensionsstabilität (Durchschnittswert) In Längsrichtung (%): In Querrichtung (%):	Stabilité dimensionnelle (valeur moyenne) En direction longitudinale (%): Dans la direction transversale (%):	Dimensionale stabiliteit (gemiddelde waarde) In lengterichting (%): In dwarsrichting (%):	Stabilità dimensionale (valore medio) In direzione longitudinale (%): In direzione incrociata (%):	✓ -0.03 -0.08
ISO 24344:2008, method A	Flexibility	Flexibilität	Flexibilité	Flexibiliteit	Flessibilità	20 mm
ISO 24343-1:2012	Residual indentation	Resteindruck	Indentation résiduelle	Restindruk	Rientranza residua	0.08 mm
ISO 4918:2016	Castor chair test	Stuhlrollentest	Test de chaise roulette	Rolstoeltest	Test della sedia a rotelle	✓
ISO 105B02:2013	Colour fastness to artificial light	Lichtechtheit (Xenotest)	Solidité des couleurs à la lumière artificielle	Kleurvastheid bij kunstlicht	Solidità del colore alla luce artificiale	6-8, depending on design
ISO 10582:2017	Usage category	Beanspruchungsklasse	Catégorie d'utilisation	Gebruikscategorie	Categoria di utilizzo	34 - Very heavy commercial use 43 - Heavy industrial use
EN 1081:1998	Electrical resistance	Elektrischer Widerstand	Résistance électrique	Elektrische weerstand	Resistenza elettrica	
	Method A, vertical resistance Method C, horizontal resistance	Verfahren A – für Durchgangswiderstand R1 Verfahren C – für Oberflächenwiderstand R3	Méthode A, résistance verticale Méthode C, résistance horizontale	Methode A, verticale weerstand Methode C, horizontale weerstand	Metodo A, resistenza verticale Metodo C, resistenza orizzontale	8.7x10 ¹⁰ Ω 8.0x10 ¹¹ Ω
EN 1815:2016, method A	Static electrical propensity (anti-static)	Elektrostatisches Verhalten (antistatisch)	Propension électrique statique (antistatique)	Statische elektrische neiging (antistatisch)	Propensione elettrica statica (antistatica)	Rubber sole: 0.4 kV
EN 13893:2002	Slip resistance (μ)	Rutschhemmung (μ)	Antidérapant (μ)	Slipweerstand (μ)	Resistenza allo scivolamento (μ)	0.4
ISO 8302:1991 EN 12667:2001	Thermal resistance (thermal conductivity)	Thermischer Widerstand (Wärmeleitfähigkeit)	Résistance thermique (conductivité thermique)	Thermische weerstand (thermische geleidbaarheid)	Resistenza termica (conducibilità termica)	0.020 m² K/W
ISO 26987:2008	Staining and resistance to chemicals	Fleckenempfindlichkeit und Chemikalienbeständigkeit	Coloration et résistance aux produit chimiques	Kleuring en weerstand tegen chemicaliën	Colorazione e resistenza agli agenti chimici	0 - no change
EN ISO 10140-1 - 5:2010	Impact sound insulation	Trittschalldämmung	Isolation phonique d'impact	Impact geluidsisolatie	Isolamento acustico	ΔL _w 8 dB
EN ISO 354:2003	Sound absorption	Schallabsorption	Absorption sonore	Geluidsabsorptie	Assorbimento acustico	α _w 0.05
EN 13501-1:2007 + A1:2009	Classification of burning behaviour	Brandverhalten	Comportement à la combustion	Brandgedrag	Comportamento alla combustione	Bfl - s1
	Underfloor heating	Fußbodenheizung	Chauffage par le sol	Vloerverwarming	Riscaldamento a pavimento	28°C



mFLOR.